

GGPR7 High Bending Strength Fiber

Product Information

* U.S. Pat No (s). Re 36,146. Licenses granted by 3M IPC

Issue Date: 2008/09

Product Name: GGPR7

FEATURES

- Based on 3M Licensed High Strength GGP fiber technology, an additional five micron permanent protective coating on the glass cladding makes it the most robust fiber in the telecommunication industry
- Macrobending loss performance compliant to ITU-T G.657 Class B single mode fiber
- Small bending fatigue lifetime is several hundred times longer than all standard single mode fiber

APPLICATIONS

- FTTH installation, Indoor cable, Drop/Distribution cable, can be used with mechanical splicer
- Low bending loss patch cords with SC, FC, LC type connectors

OPTICAL CHARACTERISTICS

Characteristics	Conditions	Specified Values	Unit
Attenuation Coefficient	1310 nm	≤ 0.4	[dB/km]
	1385 nm	≤ 0.4	[dB/km]
	1550 nm	≤ 0.23	[dB/km]
	1625 nm	≤ 0.25	[dB/km]
Mode Field Diameter	1310 nm	7.0 ± 0.4	[μm]
	1550 nm	8.0 ± 0.5	[μm]
Fiber Cut-Off Wavelength		< 1330	[nm]
Cable Fiber Cut-Off Wavelength		≤ 1260	[nm]
Zero Dispersion Wavelength		1320~1370	[nm]
Zero Dispersion Slope		≤ 0.092	[ps/(nm ² ·km)]
Dispersion Coefficient	1285 – 1330 nm	≤ 3.1	[ps/(nm·km)]
	1550 nm	≤ 18	[ps/(nm·km)]

BACKSCATTER CHARACTERISTICS

Attenuation Directional Uniformity		≤ 0.03	[dB/km]
Attenuation Uniformity		≤ 0.05	[dB]
Group Index of Refraction	1310 nm	1.47	
	1550 nm	1.47	

PHYSICAL CHARACTERISTICS

Glass Cladding Diameter		115 ± 1	[μm]
P-coat Diameter		125 ± 1	[μm]
P-coat Non-Circularity		≤ 1.0	[%]
Core/P-coat Concentricity Error		≤ 0.8	[μm]
Acrylate Coating Diameter		245 ± 10	[μm]
Coating Concentricity Error		≤ 6	[μm]
Fiber curl		≥ 2	[m]
Proof Test (Screen level)		0.69 (1.0)	[GPa] [%]
Macrobending loss at 1550 nm/1625nm(1 turn, 5 mm radius) (1 turns around a mandrel of 7.5 mm radius)		$\leq 0.5/1.0$	[dB]
		$\leq 0.05/0.1$	[dB]
Acrylate Coating Strip Force, Average / Peak Length (Typical)		$\geq 105 / 140$	[g]
		1.0~25.2	[Km]

ENVIRONMENTAL CHARACTERISTICS

Temperature Dependence at 1310 nm and 1550 nm Induced Attenuation – 40°C to +85°C		≤ 0.05	[dB/km]
Damp Heat Dependence at 1310 nm and 1550 nm Induced Attenuation at 85°C, 85%R.H., 30 days		≤ 0.05	[dB/km]

Prime Optical Fiber Corporation
 No.11, Ke Jung Rd.
 Science-Based Industrial Park
 Chu-Nan, 350, Miao-Li County, Taiwan, R.O.C.
 Tel: 886-37-586999 Fax: 886-37-586899
 E-mail: sales@pofc.com.tw

