

## Singlemode Optical Fiber

## Product Information

Issue Date: 2004/5/25

This specification conforms to the requirement of IEC 60793 B1.1 and ITU-T G.652.A/B.

### OPTICAL CHARACTERISTICS

<i>Characteristics</i>	<i>Conditions</i>	<i>Specified Values</i>	<i>Unit</i>
Attenuation Coefficient	1310 nm	$\leq 0.34$	[ dB/km ]
	1285 – 1330 nm	$\leq 0.36$	[ dB/km ]
	1550 nm	$\leq 0.21$	[ dB/km ]
Mode Field Diameter	1310 nm	8.7 ~ 9.7	[ $\mu\text{m}$ ]
Fiber Cut-Off Wavelength		1150 ~ 1330	[ nm ]
Cable Cut-Off Wavelength		< 1260	[ nm ]
Zero Dispersion Wavelength		1300 ~ 1322	[ nm ]
Zero Dispersion Slope		$\leq 0.092$	[ ps/(nm <sup>2</sup> ·km) ]
Dispersion Coefficient	1285 – 1330 nm	$\leq 3.1$	[ ps/(nm·km) ]
	1550 nm	$\leq 18$	[ ps/(nm·km) ]
PMD		$\leq 0.2$	[ ps/ $\sqrt{\text{km}}$ ]

### BACKSCATTER CHARACTERISTICS

Attenuation Directional Uniformity		$\leq 0.03$	[ dB/km ]
Attenuation Uniformity		$\leq 0.05$	[ dB ]
Reflections		Not Allowed	
Group Index of Refraction	1310 nm	1.467	
	1550 nm	1.468	

### PHYSICAL CHARACTERISTICS

Core / Cladding Concentricity Error		$\leq 0.8$	[ $\mu\text{m}$ ]
Cladding Diameter		125 $\pm$ 1	[ $\mu\text{m}$ ]
Cladding Non-Circularity		$\leq 2.0$	[ % ]
Coating Diameter (UV Curable Acrylate)		245 $\pm$ 10	[ $\mu\text{m}$ ]
Clad/Coat Concentricity Error		$\leq 6$	[ $\mu\text{m}$ ]
Fiber curl		$\leq 4$	[ m ]
Proof Test		100	[ kpsi ]
Bend Induced Attenuation at 1550 nm (100 turns around a mandrel of 60 mm diameter)		$\leq 0.1$	[ dB ]
Fatigue Resistance Parameter (nd)		20	
Average Coating Strip Force / Peak Coating Strip Force		$\geq 105 / 140$ (1.4)	[ g ] / (N)
Length (Typical)		12.6 ~ 25.2	[ km ]

### ENVIRONMENTAL CHARACTERISTICS

Temperature Dependence at 1310 nm and 1550 nm Induced Attenuation – 60°C to +85°C		$\leq 0.05$	[ dB/km ]
Watersoak Dependence at 1310 nm and 1550 nm Induced Attenuation at 20°C for 30 days		$\leq 0.05$	[ dB/km ]
Damp Heat Dependence at 1310 nm and 1550 nm Induced Attenuation at 85°C, 85%R.H., 30 days		$\leq 0.05$	[ dB/km ]

Prime Optical Fiber Corporation  
 No.11, Ke Jung Rd.  
 Science-Based Industrial Park  
 Chu-Nan, 350, Miao-Li County, Taiwan, R.O.C.  
 Tel: 886-37-586999 Fax: 886-37-586899  
 E-mail: sales@pofc.com.tw

